

TECHNICAL DATA SHEET

EFIRON[®] Polymer Clad
Series

SPC-404AP

FOSPIA
OPTICAL SOLUTIONS

FOSPIA CO., LTD

53, Jiwon-ro, Danwon-gu, Ansan-si, Gyeonggi-do, Korea
Tel) +82-31-365-3680 Fax) +82-31-365-3681
<http://www.fospia.com>

CONTENTS

- A. MATERIAL DESCRIPTION

- B. MATERIAL PROPERTIES
 - 1. Liquid
 - 2. Cured

A. MATERIAL DESCRIPTION

EFIRON[®] SPC-404AP coating is a radiation-curable acrylate useful for polymer cladding making processes. EFIRON[®] SPC-404AP coating has suitable glass transition temperature, rapid cure property, non-yellowing, thermal resistance, high oxidative and hydrolytic (moisture) stability, which are required by optical fiber industry applications.

1. CURING CONDITION

Minimum UV dose of EFIRON[®] SPC-404AP for complete cure is minimum 1000 mJ/cm² under a nitrogen environment. However, the minimum dosage is heavily dependent upon the thickness of the PC layer.

2. STORAGE

EFIRON[®] SPC-404AP polymer cladding coating can polymerize under improper storage conditions. Store materials away from direct sunlight and presence of oxidizing agents and free radicals. Storage temperature range is between 10°C to 30°C.

3. PRECAUTION

EFIRON[®] SPC-404AP polymer cladding coating materials can cause skin and eye irritation after contact. Therefore, avoid direct contact with these materials. If contact occurs, immediately rinse affected areas copiously with water.

4. NOTES

The information contained herein is believed to be reliable but is not to be taken as representation, warranty or guarantee and customers are urged to make their own tests.

B. MATERIAL PROPERTIES

1. LIQUID

Viscosity	at 25 °C	4,800 cPs
Density	at 20 °C	1.52 g·cm ⁻³
Refractive Index	at 25°C, 589 nm	1.396

2. CURED

Refractive Index at 852 nm	1.404
Glass Transition Temperature	
At Tan_delta Max	103 °C
Secant Modulus	
At 2.5% Strain	410 MPa
Young's Modulus	540 MPa
Tensile Strength at Break	23 MPa(In Testing)
Elongation at Break	15 %(In Testing)
Shrinkage on Cure	<10.0 %

The information contained herein is believed to be reliable but is not to be taken as a representation, warranty or Guarantee. Customers are urged to perform their own process and QC tests.