

TECHNICAL DATA SHEET

EFIRON[®] SCU-2000

FOSPIA CO., LTD

53, Jiwon-ro, Danwon-gu, Ansan-si, Gyeonggi-do, Korea
Tel) +82-31-365-3680 Fax) +82-31-365-3681
<http://www.fospia.com>

CONTENTS

- A. MATERIAL DESCRIPTION**
- B. MATERIAL PROPERTIES**
 - 1. Liquid Coating**
 - 2. Cured Coating**

A. MATERIAL DESCRIPTION

EFIRON[®] SCU-2000 is Single coating for Glass Optical fiber. EFIRON[®] SCU-2000 has suitable glass transition temperature, rapid cure property, free-point lump, water and chemical resistance, low volatilization, high oxidative and hydrolytic (moisture) stability which are required by optical fiber industry application.

1. CURING CONDITION

EFIRON[®] SCU-2000 has cure speed so it can be applied to 1,000 m/min line. The minimum UV dose for complete cure is about 1 J/cm² (UV-A range) under the nitrogen environment.

2. STORAGE

EFIRON[®] SCU-2000 can be polymerized under improper storage conditions. Store materials away from direct sunlight and presence of oxidizing agents and free radicals. Storage temperature range is between 10°C to 30°C.

3. PRECAUTION

EFIRON[®] SCU-2000 can cause skin and eye irritation after contact. Therefore, avoid direct contact with these materials. If contact occurs, immediately rinse affected areas copiously with water.

4. NOTES

The information contained herein is believed to be reliable but is not to be taken as representation, warranty or guarantee and customers are urged to make their own tests.

1. Liquid Coating

Viscosity	at 25 °C	10,000 cPs
Density	at 23 °C	1.12g·cm ⁻³
Refractive Index	at 25°C	1.496

2. Cured Coating

Test at <1% R.H

Glass Transition Temperature	
at Tan_delta Max	In Testing

Test at 23 °C, 50% R.H

Secant Modulus at 2.5% Strain	260 MPa
Tensile Strength	23 MPa
Elongation	40 %
Refractive Index at 852nm	1.501
at 1550nm	1.492

* Film preparation in Test A of EFIRON® test methods :

75 µm film thickness, D-bulb, 1.0 J/cm² (UV-A Range: 315–400nm) with Nitrogen Box